

AMENDMENTS TO THE CLAIMS

1. (Currently Amended) A ring-opened polymer hydrogenated product containing a repeating unit originating from a polycyclic norbornene monomer with three or more rings in the polymer repeating units, having a weight average molecular weight of 25,000 to 1,000,000, and having a racemo diad proportion of ~~[[51%]]~~ 70% or more.

2. (Cancelled)

3. (Original) The ring-opened polymer hydrogenated product according to claim 1, wherein the content of the repeating unit originating from a polycyclic norbornene monomer with three or more rings is 50 mol% or more.

4. (Original) The ring-opened polymer hydrogenated product according to claim 1, wherein the repeating unit originating from a polycyclic norbornene monomer with three or more rings is a repeating unit originating from dicyclopentadiene.

5. (Original) The ring-opened polymer hydrogenated product according to claim 1, which is a crystalline polymer.

6. (Original) The ring-opened polymer hydrogenated product according to claim 5, which is a polymer having a melting point of 150°C or more.


7-9. (Cancelled)

10. (New) A process for producing the ring-opened polymer hydrogenated product according to claim 1, comprising a step of polymerizing a polycyclic norbornene monomer having three or more rings by solution polymerization using a compound shown by the following formula (a) as a polymerization catalyst to obtain a ring-opened polymer and a step of hydrogenating double bonds in the main chain of the ring-opened polymer,



wherein M is tungsten, R^a is a substituted or unsubstituted phenyl group with a substituent at any of 3, 4, or 5 position or a group represented by $-CH_2R^d$, wherein R^d indicates a hydrogen atom, a substituted or unsubstituted alkyl group, or a substituted or unsubstituted aryl group, X represents a halogen atom, alkyl group, aryl group, or alkylsilyl group, Y is a hydroxyl group-containing aryloxy group or a hydroxyl group-containing alkoxyl group, L is an electron donating neutral ligand, and b is an integer of 0 to 2.

11. (New) A process for producing the ring-opened polymer hydrogenated product according to claim 1, comprising a step of polymerizing a polycyclic norbornene monomer having three or more rings by solution polymerization using a compound shown by the following formula (b) as a polymerization catalyst to obtain a ring-opened polymer and a step of hydrogenating double bonds in the main chain of the ring-opened polymer,



wherein M is tungsten, R^b is a substituted or unsubstituted phenyl group with a substituent at any of 3, 4, or 5 position or a group represented by $-CH_2R^d$, wherein R^d indicates a hydrogen atom, a substituted or unsubstituted alkyl group, or a substituted or unsubstituted aryl group, X represents a halogen atom, alkyl group, aryl group, or alkylsilyl group, R^c is a substituted or unsubstituted alkyl group or a substituted or unsubstituted aryl group, L is an electron donating neutral ligand, a is 0 or 1, and b is an integer of 0 to 2.